

Ceramic bowl for Gold melting

Model	outer diameter (Φ)	Height(H)	Capacity (kg)	per Carton (pc)
SBA-001	53	20	0.1	400
SBA-002	61	21	0.15	350
SBA-003	69	24	0.25	280
SBA-004	80	32	0.4	200
SBA-005	86	36	0.5	160
SBA-006	95	37	0.75	120
SBA-007	107	40	1	80
SBA-008	107	48	1.5	64
SBA-009	140	56	2.5	42
SBA-010	160	62	5	36
SBA-011	180	70	10	24

Picture


SCJceramic.com
 Laboratory ceramic



www.scjceramic.com

Email: Yolanda@scjceramic.com

PARAMETER		Ceramic Crucibles are used in various purposes - 1) Metal melting 2) Gold & Silver Melting 3) Labware 4) Testing equipment
Main ingredient :	SiO ₂	
Purity :	99.90%	
density:	1.9g/cm ³	
Bending strength:	60 (Mpa)	
Hardness:	60	